

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08K 5/10, 5/11, C08L 31/02, 33/04	A1	(11) International Publication Number: WO 95/01392 (43) International Publication Date: 12 January 1995 (12.01.95)
(21) International Application Number: PCT/US94/07330 (22) International Filing Date: 29 June 1994 (29.06.94) (30) Priority Data: 086,235 1 July 1993 (01.07.93) US (60) Parent Application or Grant (63) Related by Continuation US 086,235 (CON) Filed on 1 July 1993 (01.07.93) (71) Applicant (for all designated States except US): THE GILLETTE COMPANY [US/US]; Prudential Tower Building, Boston, MA 02199 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): LOFTIN, Rachel, M. [US/US]; 9 Doris Road, Halifax, MA 02338-1149 (US). (74) Agents: HANDELMAN, Joseph, H. et al.; Ladas & Parry, 26 West 61st Street, New York, NY 10023 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: OVERHEAD PROJECTOR INKS (57) Abstract A dry-wipeable overhead projector film ink is provided which includes a colorant, an acrylic polymer having a film forming temperature below room temperature, and water. Preferred inks further include a surfactant and an anti-drying agent. The inks are easily removable from most types of overhead projector film by wiping with a dry cloth or fingertip. Certain preferred inks are also removable by wiping with a wet cloth.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

OVERHEAD PROJECTOR INKS

This invention relates to ink compositions.

Overhead projectors are widely used, particularly in academic and business settings. Overhead projectors enable a marking on a transparent film to be projected on a screen or wall by shining light through the transparent film. A speaker giving a presentation can write on the transparent film, and/or make additions or corrections to a preprinted image, while the film is on the overhead projector. This allows the speaker a flexibility which would not be possible if transparencies or other audiovisual aids were used.

Conventional inks for use on overhead projector (OHP) film fall into two categories: permanent OHP inks and erasable OHP inks. Most erasable OHP inks are "washable," i.e., water is required to remove a marking made with the ink. This can make removal of the markings messy and inconvenient, and also can make it difficult to erase a small portion of a marking.

The invention features aqueous inks for use in marking overhead projectors. These inks form markings of excellent quality and light transmission on, and are readily removable

- 2 -

from most commercially available overhead projector films. The inks are dry-wipeable, i.e., a marking made on an overhead projector film with the ink may be removed, after drying, by wiping the marking with a dry cloth (i.e., a cloth, felt eraser, tissue, or the like). Advantageously, by dry wiping, a small area of a marking can be easily removed, without interfering with the rest of the marking.

10 Markings made with preferred compositions may also be removed by the user by wiping the marking with a fingertip. Further, the markings formed with the inks wipe off cleanly, with minimal dust formation, and resist inadvertent

15 removal, e.g., when sheets of OHP film are shuffled together or photocopied. Some preferred compositions are also water wipeable, as well as dry-wipeable.

The inks of the invention include a colorant, a polymer having a film-forming temperature below room temperature, and water.

In preferred compositions, the polymer is an acrylic polymer, preferably provided in the form of an emulsion. The acrylic polymer

25 preferably has a glass transition temperature (T_g) of from about +20°C. to -40°C. and a film forming temperature below room temperature (25°C.), preferably below 20°C. Preferably, the ink further includes a surfactant, more

30 preferably a silicone surfactant, and an anti-drying agent, more preferably a humectant, most preferably glycerol.

The term "film forming temperature," as used herein, refers to the temperature at which the film forming polymer forms a

35 continuous dry film. The term "glass transition temperature," as used herein, refers to the

- 3 -

temperature at which the mobility of randomly cited long chain molecules in the film forming polymer is lost.

It has been found that, by adjusting the pH of the ink composition, the ink can be rendered washable as well as dry-wipeable. Accordingly, if washability is desired, the compositions further include a base, e.g., a buffer. Preferably, sufficient base is added to adjust the pH of the ink composition to from about 7 to 10.

Preferred compositions may also include a peeling agent, e.g., a latex polymer, to enhance removability of the dry marking, and/or a fluoropolymer, to extend the period of time over which the marking remains dry-wipeable.

Other features and advantages of the invention will be apparent from the description of the preferred embodiments and from the claims.

Preferred marker inks include a surfactant, an acrylic film-forming polymer, an anti-drying agent, a pigment, and water.

The surfactant is preferably a silicone surfactant. Suitable silicone surfactants include, but are not limited to, silanes and siloxanes. Preferred silicone surfactants are polyalkylene oxide-modified methylpolysiloxanes, e.g., those commercially available from Union Carbide under the tradename SILWET. Preferred compositions contain from about 0.-1 to 5 weight percent surfactant, more preferably from about 0.5 to 2 weight percent. Lower levels may reduce wetting of the OHP film by the ink, while higher levels may cause too much adhesion of the ink to the film.

- 4 -

The acrylic polymer is preferably provided in the form of an emulsion. Typical emulsions have a solids level of about 50%. If desired, a water soluble acrylic may be used and predissolved in the water which will be contained in the ink composition. Preferred acrylic polymers have a glass transition temperature of from about +20°C. to -40°C. and a film forming temperature below room temperature, more preferably below 10°C. Preferred acrylic polymers include those commercially available under the tradename G-CRYL from Henkel Corp., and the tradename ACRY SOL from Rohm & Haas. Particularly preferred acrylic emulsions are G-CRYL 1200 and ACRY SOL I-1955. Preferred compositions contain from about 5 to 15 weight percent of the acrylic polymer. Too much of the acrylic may result in undesirably high viscosity at an effective level of resin and may reduce the removability of the dried marking, while too little may result in an ink which does not form a coherent film on all overhead projector films.

The anti-drying agent is preferably a humectant, more preferably glycerol. Glycols are typically less preferred, as they may cause smearing when the marking is dry-wiped. The anti-drying agent prevents dry-out of a marker containing the ink when its cap is left off, and also significantly enhances removability of the dried marking. Too much of the anti-drying agent may cause the ink to dry too slowly, while too little may not prevent drying out of the marker and may reduce removability. Preferred compositions include from 1 to 25 weight percent of the humectant, preferably from about 5 to 20 weight percent.

- 5 -

Enough pigment should be included in the ink to provide an adequate color intensity, but not so much that light transmission is compromised. The preferred inks include between
5 approximately 2% and 20% pigment by weight, more preferably between approximately 5% and 10%. Pigments that may be used in the invention include water dispersible pigments, and preferably the pigment is provided in the form
10 of an aqueous dispersion, for accurate measurement and uniform mixing. Preferred pigment dispersions contain an acrylic dispersant, as these dispersions are most compatible with the acrylic polymer component of
15 the composition. Suitable pigment dispersions are available from HeucoTech, under the tradename HEUCOSPERSE III. It is preferred that the pigment have a relatively small particle size, preferably less than 0.5 micron, to
20 prevent settling and for use in capillary feed markers.

Sufficient water should be included in the ink so that its Brookfield viscosity at 25°C. is less than about 20 cps, more preferably
25 between about 2 cps and 10 cps. If the viscosity is too low, the composition may not contain effective amounts of the active ingredients. If the viscosity is too high, the ink may be too thick for practical use,
30 particularly in capillary feed systems.

Preferred compositions may, optionally, include a small amount of a peeling agent, to enhance the removability of the dried marking. Preferred peeling agents are latex
35 polymers, more preferably styrene butadiene rubber (SBR) latexes. A suitable SBR latex is available from Goodyear under the tradename

- 6 -

PLIOLITE. It is preferred that the composition contain from about 0 to 5 weight percent of the SBR latex. Too much of the peeling agent may cause a marking made with the ink to be crumbly or smeary.

Preferred compositions may also include a base, e.g., a buffer, if it is desired that markings formed by the ink be water washable as well as dry-wipeable. Acid stabilized acrylic emulsions are generally preferred for optimal washability with a wide variety of bases. A suitable emulsion is ACRYSOL I-1955 emulsion, available from Rohm and Haas. Suitable buffers include but are not limited to potassium hydroxide, sodium hydroxide, sodium carbonate and 2-amino-2-methyl-1-propanol. Preferred washable compositions contain from about 0.1 to 5 weight percent of the buffer. The preferred amount will depend upon the strength of the base selected and the initial pH of the composition. Preferably, a sufficient amount is included to bring the pH of the ink to about 7 to 10.

Markings made with the preferred inks typically become permanent after a period of time, e.g., a week after the marking is made. This may be advantageous, if the user desires to store the marked OHP film for future use. However, if it is desired that markings made with the ink remain dry-wipeable over long periods, a fluoropolymer may be added to the ink to enhance long-term removability. A suitable fluoropolymer is available from Eastern Color and Chemical under the tradename RANE-OFF F-7. Preferred compositions contain from about 1 to 10 weight percent fluoropolymer.

Other conventional ingredients may be

- 7 -

included in the composition, e.g., biocides.

A preferred procedure for preparing the compositions of the invention is to add the surfactant to the water, then add the acrylic
5 emulsion, then the anti-drying agent, and finally the pigment dispersion, mixing between each addition. The order of addition is not critical however, and other procedures can be used, as is well known in the art. The
10 ingredients can be mixed using any conventional mixer, under conditions of relatively low shear.

The following examples illustrate the invention.

EXAMPLE

15 Three preferred compositions are shown in Table 1. These compositions were used in capillary feed markers to form a series of markings on polyethylenes. Markings made with all three compositions were readily removable by
20 wiping with a dry cloth, and by wiping with a fingertip. Markings made with composition 1 were also removable by wiping with a wet cloth. The markings which were not immediately removed were left for four days and then wiped with a
25 dry cloth. The markings made with compositions 1 and 2 were not removable, i.e., had become permanent, while the marking made with composition 3 remained removable.

TABLE 1

Component	Amount (%)		
	1	2	3
ACRYSOL I-1955 emulsion	25	-	-
G-CRYL 1224 emulsion	-	20	-
ACX 12-903 emulsion	-	-	20
HEUCOSPERSER III B8 5520 pigment dispersion	20	18	16
Glycerol	10	15	10
2-amino-2-methyl-1-propanol	1	-	-
SILWET L7001 surfactant	0.5	0.5	0.5
SILWET L7604 surfactant	0.5	0.5	0.5
RANE-OFF F7 fluoropolymer	-	-	2
Water*	43	46	51

* (In addition to water in emulsion and pigment dispersion)

- 9 -

Other embodiments are within the claims.. For example, preferred inks may also be used on other types of plastic film, e.g., polystyrene and acetate films.

- 10 -

C L A I M S

1. A method of marking an overhead projector film, comprising:
making a marking on the overhead projector film with an ink comprising a colorant, a polymer having a film-forming temperature below room temperature, and water.
2. The method of claim 1, further comprising the step of removing the marking from the film by wiping the marking with a dry tissue or cloth.
3. The method of claim 1, wherein the polymer has a glass transition temperature of from about +20°C. to -40°C.
4. The method of claim 1, wherein said polymer is an acrylic polymer.
5. The method of claim 1, wherein said ink further comprises a surfactant.
6. The method of claim 1, wherein said ink further comprises an anti-drying agent.
7. The method of claim 1, wherein said ink comprises from about 0.1 to 5 weight of a surfactant, from about 2 to 20 weight percent of said colorant, from about 2 to 20 weight percent of said polymer, and from about 1 to 25 percent of an anti-drying agent.
8. The method of claim 1, wherein the polymer has a film forming temperature below 10°C.
9. The method of claim 5 or 7, wherein said surfactant is a silicone surfactant.
10. The method of claim 6 or 7, wherein said anti-drying agent is glycerol.
11. The method of claim 1, wherein the ink further comprises a base.
12. The method of claim 11, wherein said ink contains a sufficient amount of base to

- 11 -

adjust the pH of the ink composition to from about 7 to 10.

13. The method of claim 11, wherein the polymer is acid-stabilized.

5 14. The method of claim 11, further comprising the step of removing the marking from the film by wiping the marking with a damp cloth.

15. The method of claim 1, wherein said ink further comprises a peeling agent.

16. The method of claim 15, wherein said peeling agent is a latex polymer.

17. The method of claim 1, wherein said ink further comprises a fluoropolymer.

15 18. A dry-wipeable overhead projector film ink comprising a colorant, an acrylic polymer having a film forming temperature below room temperature and water.

19. An ink of claim 18, wherein said colorant is a pigment.

20. An ink of claim 18, wherein the acrylic polymer is provided in the form of an emulsion.

21. An ink of claim 18, wherein the acrylic polymer has a glass transition temperature (T_g) of from about +20°C. to -40°C.

22. An ink of claim 18, further comprising a surfactant.

23. An ink of claim 18 or 22, further comprising an anti-drying agent.

24. An ink of claim 18, wherein the acrylic polymer has a film-forming temperature below 10°C.

25. An ink of claim 22, wherein the surfactant is a silicone surfactant.

26. An ink of claim 23, wherein the anti-drying agent is a humectant.

- 12 -

27. An ink of claim 26, wherein the humectant is glycerol.
28. An ink of claim 18, wherein the ink further comprises a base.
- 5 29. An ink of claim 28, wherein said base is a buffer.
30. An ink of claim 28, wherein said acrylic emulsion is acid-stabilized.
31. An ink of claim 28, wherein said ink
10 contains a sufficient amount of base to adjust the pH of the ink composition to from about 7 to 10.
32. An ink of claim 18, further comprising a peeling agent.
- 15 33. An ink of claim 32, wherein said peeling agent is a latex polymer.
34. An ink of claim 18, further comprising a fluoropolymer.
35. An ink of claim 23, comprising from
20 about 0.1 to 5 weight percent of a surfactant, from about 2 to 23 weight percent of said colorant, from about 2 to 23 weight percent of said acrylic polymer, from about 1 to 28 weight percent of an anti-drying agent, and sufficient
25 water to provide a viscosity of less than about 20 cps.
36. A method of marking an overhead projector film, comprising:
making a marking with an ink
30 comprising a colorant, an acid-functional polymer, a base, and water; on the overhead projector film;
wherein the marking is capable of being removed by wiping the marking with a dry
35 cloth or tissue.
37. The method of claim 36, wherein said ink has a pH of from about 7 to 10.

- 13 -

38. The method of claim 36, further comprising the step of removing said marking by wiping said marking with a damp cloth.

39. The method of claim 36, wherein said
5 polymer has a film forming temperature below room temperature.

40. The method of claim 39, further comprising the step of removing said marking by wiping said marking with a dry cloth.

10 41. The method of claim 36, wherein said polymer is an acrylic polymer.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/07330

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : C08K 5/10, 5/11; C08L 31/02, 33/04

US CL : 524/312, 317, 556

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/312, 317, 556

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US, A, 4,097,289 (HOFMANN ET AL) 27 June 1978 Columns 1-2.	1-41
X	US, A, 4,935,461 (NAKAMURA) 19 June 1990, columns 2-3 and the Examples.	1-41
X	US, A, 4,940,628 (LIN ET AL) 10 July 1990, columns 3-4 and the Examples.	1-41

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 19 AUGUST 1994	Date of mailing of the international search report 14 SEP 1994
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230	Authorized officer JEFFREY SMITH Telephone No. (703) 308-2351